

**TEST REPORT: 7191245785-CHM20-05-RC**  
19 OCT 2020



PSB Singapore

**RESULTS**

Sample Description: Enro – Tech 3D fabric (after 100 washes)

Test Method:  
ASTM F2101 (modified)

Test sample/ controls	Stage 1, CFU	Stage 2, CFU	Stage 3, CFU	Stage 4, CFU	Stage 5, CFU	Stage 6, CFU	Sum of Total plate count for the 6 sieves, CFU	Average Count for Controls, CFU	VFE (%)
-ve Control	0	0	0	0	0	0	Less than 1		
+ve Control 1	131	450	448	439	481	149	2098	2117	
+ve Control 2	141	448	453	418	495	181	2136		
Sample 1	0	0	0	0	0	5	5		99.76
Sample 2	0	0	0	0	0	4	4		99.81
Sample 3	0	0	0	0	0	4	4		99.81
Sample 4	0	0	0	0	0	3	3		99.86
Sample 5	0	0	0	0	0	3	3		99.86